

## TECHNICAL SHEET

### CBP – Cabine protect pro

#### Description

Transparent protection coating (waterborn). Forms a static coat to collect en keep dust particles and paint overspray. Washable with water.

#### Properties

Heat resistant	65 C°
Viscosity	standard 1000-1300 cps with SP5 / 100T/min Brookfield RVT
pH	+/- 8-9
Specific weight	1,12 g / cm <sup>3</sup>
Film	transparent, sticky
Return	15 to 20m <sup>2</sup> / liter/layer

#### Application

Cabine protect is a waterbased dispersion that complies with environmental norms, security & health standards. This product is stabilized with a system of biodegradable surface active substances and contains no plasticizers.

The product is only used on hardened undergrounds as sticky coating. Specific application on walls of spraybooths existing in aluminium/inox, galvanised and varnished walls.

#### Instruction for use

##### Spray gun

Use a 2.5 nozzle or airmix or airless. Spray pressure: 2-3 bar. Layer thickness: 125 µm.  
The layer thickness determines how fast the product dries out. For an optimal application we recommend to apply the product in 3 layers. After applying a layer wait 20 minutes before applying another.  
Cabin 7 x 4 x 3: average consumption 12L

##### Brush/roll

To prevent the coating from dripping, apply a thin smooth layer on vertical surfaces.

Do not use at a temperature under 5°C.

**ATTENTION:** at often rising temperatures (>65C°), Cabine protect dries faster.

#### Maintenance

The ease of removing the product strongly depends on the thickness of the applied layers, the temperature in the spray cabin, the frequency the cabin is used and the period of time the product has been on the walls.

For intensive use: (more than 5 times a day) we recommend to apply an extra layer on the existing layer once a month, in order to re-activate the effects. When the product doesn't stick anymore wash all layers with water and apply 3 new layers, as described above.

## **Safety regulations**

Avoid contact with the skin. Wash your hands after use.  
In case of eye contact: rinse with water.

## **Opslag en houdbaarheid**

KEEP FROM FROST, do not store above 40°C

Shelf life: +/- 6 months in closed package

Do not use at a temperature underneath 5°C.

**ATTENTION:** at often rising temperatures (>65C°), Cabine protect dries faster.

*The above information is given in good faith, but the user should assure himself that the performance of the product is sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Chemicar Europe cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the products suitability for their own applications.*