










TECHNICAL SPRAYS

General information



		DESCRIPTION	 NUMBER OF COATS	 FLASH BETWEEN COATS (min.)	 DRY FILM THICKNESS	 DUST DRY (min.)	 DRYING (min.)	 DRYING IR (min.)	 SHELF LIFE (year)	 M ² /CAN/LAYER	 PAGE
PRIMER/ FILLER	TSP 110 - 120 - 130 - 140	Universal Primer/filler	1-2	10	30µm	10	60 - 20°C	10	2	1,5	129
	TSP 150	UV Primer/Filler	1-2	until matt	30-40µm	-	3-5 - UV	-	2	1,5	129
	TSP 1200	UV Primer cleaner	-	-	-	-	-	-	2	-	129
CORROSION PROTECTION	TSP 190	Etch primer	1-2	3-5	15µm	5	20 - 20°C	-	2	-	130
	TSP 410	Zinc spray	1-4	10	20-25µm	10	20 - 20°C	-	-	1-2	130
	TSP 810	Weld thru primer - Zinc phosphate	2	5	-	-	15 - 20°C	-	1	-	131
	TSP 530	Weld thru primer - Copper	2	5	-	-	10 - 20°C	-	1	-	131
PAINTS & LACQUERS	TSP 520 - 525	Wheel spray	2-3	5	-	10	180 - 20°C	possible	1	-	132
	TSP 180	1K clear coat	2-3	10	30-40µm	10	120	-	5	1,3-1,4 40µm	132
	TSP 1000 - 1010	High gloss	-	10	-	10	120	-	-	1,5	132
	TSP 910	Matt black	2-3	5	15-20µm	10	300 - 20°C	-	-	1-2	132
2K	TSP 710	2K clear coat	1-2	10-15	30-50µm	10	720 - 20°C 40 - 60°C	35-40	2	0,5 - 0,75	138
	TSP 720	2K spray putty	2-5	5	200-450µm	15	300 - 20°C 30 - 60°C	20-40	2	0,25 200µm	138
SPECIALS	TSP 030	Adhesion promotor	Increases the adhesion on plastic. Apply in thin layer. Flash-off 10-15 minutes.								133
	TSP 310	Sanding guide	Can be sanded after 3 seconds without clogging the sanding material.								134
	TSP 920	Fade out thinner	Solvent for universal blending. Compatible with all A-brand clear coats.								133
	TSP 550	Structure spray	Restores the structure of damaged external and internal elements. Is paintable.								134
	TSP 1100	Contact glue	Universal, fast-drying spray adhesive.								134
	AGB - AGG	Anti-gravel coating	Quick-drying, paintable, anti-chip coating based on synthetic rubber.								135
	TSP 930	Control spray	Creates a temporary shine on the sample plate. For colour inspection.								136
	TSP 100 - 900	Prefill solvent-based	Can prefilled with propellant. Compatible with most paint brands.								137