



															TOEPASSING	
		BREEDTE mm	LENGTE m	KLEUR	TEMP. BESTENDIG 10 min.	TEMP. BESTENDIG 30 min.	TEMP. BESTENDIG 60 min.	VERF OP WATER BASIS	VERF OP SOLVENT BASIS	RUG SW g / m ²	DIKTE mm	TREKSTERKTE N / 25 mm	VERLENGING %	AFPEL- KLEEFKRACHT N/25mm		PAGINA
MASKEREN	MST 9	19 25 30 38 50	50		100 °C.	80°C.	60°C.			58	0.125	85	7.5	4.3	Algemene toepassingen	110
	MST 4	19 25 38 50	50		110°C.	100°C.	80°C.			62	0.132	105	10	4.6	Rondingen	110
	MST 7	19 25 30 38 50	50		120°C.	90°C.	80°C.			63	0.130	90	8	4.8	Waterbasis	111
	MST 8	19 25 38 50	50		130°C.	100°C.	100°C.			35	0.08	82.5	4	4.8	Rechte lijnen en op rubbers	111
FINE LINE	FOL 303M - 325M	3 6 9 12 15 19 25	33		140°C	140°C	140°C			33.6	0.163	215	600	4	Extreme rondingen en aflijningen	119