

### TECHNICAL SHEET

**POP 514 – Finixa foam pad 145/30mm white 2p.**

**POP 714 – Finixa foam pad 145/30mm orange 2p.**

**POL 914 – Finixa foam pad 145/30mm black 2p.**

TYPE OF FOAM	DENSITY KG/M <sup>3</sup>	TENSILE STRENGTH kPa	ULTIMATE ELONGATION %	COMPRESSION RESISTANCE kPa	NUMBER OF CELLS C/CM ppi
Foam white Standard specified value	36 - 41	200	250	8 - 11	16
Foam orange Standard specified value	34 - 42	340	160	6,4-9,6	18 - 24
Foam black Standard specified value	27 - 33	—	...	2,5 - 4,5	75 - 90

*The above information is given in good faith, but the user should assure himself that the performance of the product is sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Chemicar Europe cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the products suitability for their own applications.*