

RESISTANCE LIST : LSP 20 - 202

LEGEND

V : resistant

X : non resistant

NOTE

the information in this list serves as a reference only and can not be guaranteed! For accurate information on resistance, a resistance test must always be carried out!

	LSP 20	LSP 202
A		
acetone	X	V
acetophenome	X	V
acetylacetone	X	V
acetylen, ethee	V	V
alums	V	V
methyl formate	X	V
amyl acetate	X	V
amyl alcohol	V	V
aromat. Fuels 50% (fuel C)	V	X
B		
benzaldehyde	X	V
petrol	V	X
benzyl benzoate	V	X
benzene	V	X
benzyl alcohol	V	V

	LSP 20	LSP 202
hypochlorite 12,5%	V	V
brake fluid	X	V
butanol (butyl alcohol)	V	V
butanone(methyl ethyl ketone, MEK)	X	V
butyl acetate	X	V
butyl glycol	X	V
C		
calcium hydroxide	V	V
calcium hypochlorite	V	V
cyclohexane	V	X
cyclohexanol	V	X
cyclohexanone	X	V



	LSP 20	LSP 202
D		
denatured alcohol	V	V
diacetone	X	V
dibutyl ether	X	V
dibutyl phthalate (palatinol C)	X	V
dichloromethane (methylene chloride)	V	X
diesel fuel	V	X
diethylene glycol	V	V
dimethylphthalat	V	V
diphenyl (biphenyl)	V	X
E		
glacial acetic acid (acetic acid 100%)	X	V
petroleum	V	X
vinegar (5%aqueous acetis acid)	V	V
concentrated acetic acid (glacial)	X	V
ethanol (ethyl alcohol)	X	V
ethanolamine	X	V
ethyl acetate	X	V
ethylbenzene	V	V
ethyl chloride	V	V
ethylene glycol	V	V
2-ethyl-1-hexanol (isooctanol)	V	V
F		
paint thinner	V	X
hydrogen fluoride (hydroflouric acid)	X	V
hydroflouric acid <65% cold	V	V
formaldehyde	X	V
furan	X	X
furfuryl alcohol	X	V
G		
transmission oil	V	X
glycerol	V	V

	LSP 20	LSP 202
glycol (ethylene glycol)	V	V
H		
heating oil	V	X
n-heptane	V	X
n-hexane	V	X
Methanol	X	V
hydraulic oil	V	X
I		
isobutyl alcohol (isobutanol)	V	V
isooctane	V	X
isopropanol (isopropyl alcohol)	V	V
K		
potassium hydroxide 50%	X	V
potassium hydroxide solutions	V	V
kerosene	V	X
pine oil	V	X
neatsfoot oil	V	V
L		
paints	V	X
paints solvents	X	X
lavender oil	V	X
linseed oil	V	X
linoleic acid	V	X
M		
methanol	X	V
methyl butyl ketone	X	V
methyl ethyl ketone (butanone, MEK)	X	V
methyl isobutyl ketone (MIBK)	X	X
methyl methacrylate	X	X



	LSP 20	LSP 202
mineral oils	V	X
N		
naphtha	V	X
naphthalene	V	X
sodium hydroxide (caustic soda)	V	V
sodium hypochlorite	V	X
nitrobenzene	V	X
notromethane	V	V
notrotoluene	X	X
O		
olive oil	V	V
oxalic acid	V	V
ozone	V	V
P		
perchloric acid , 2molar	V	V
phenyl ethyl ether	X	X
phosphoric acid 3-molar	V	V
propane	V	X
propanol	V	V
R		
Castor oil A371	V	V
S		
nitric acid 3-molar	V	V
concentrated acetic acid (glacial)	V	X
hydrochloric acid for 3 molar	V	X
--> concentrated	V	X
silicone oils	X	V
soda (sodium carbonate)	V	V
super gasoline	V	X
sulfuric acid 3-molar	V	V

	LSP 20	LSP 202
-->concentrated	V	X
sulfurous acid	V	V
T		
turpentine	V	X
terpineol	V	X
tetrahydrofuran	X	V
toluene A568	V	X
transformer oil	V	X
triethanolamine	X	V
trinitrotoluene	V	X
W		
detergent dissolved in water	V	V
hydrogen peroxide diluted	V	V
Hydrogen peroxide 90%	V	X
white oil	V	X
X		
xylene	V	X
Z		
citric acid	V	V

