



TDS

TECHNICAL DATA SHEET

TECHNICAL SHEET

MSF 2xxxx - Finixa premium+ spray foil - paint adhesive

Properties

Colour:	White/transparent	
Film:	HDPE	
Density:	0.944 g / cm ³	DIN EN 1183
Thickness:	11 µm	GPA (Thickness Profile)
Tensile strength <i>machine direction</i> :	45 N / mm ²	ASTM D882
Tensile strength <i>transverse direction</i> :	30 N / mm ²	ASTM D882
Stretch strength <i>machine direction</i> :	200 %	ASTM D882
Stretch strength <i>transverse direction</i> :	450 %	ASTM D882
Dart Drop:	40gr	ASTM 1709-91
Corona treatment:	Yes	
Moisture absorbing:	No	
Heat resistant up to:	125°C	
Dimensions:	See table below	

References to storage and shelf life

Shelf life	2 years
Storage temperature:	+ 20°C / ± 10°C
Relative humidity:	30-90%
Storage:	in an enclosed space
Avoid exposure to UV:	to be avoided

Overview

Reference	Length	width	Net weight	Sales unit	Number in packaging	Number per pallet	Country of origin
MSF 24015	150M	4.0M	10.60	1.00	1.00	30.00	EU

The above information is given in good faith. However, the user's attention is drawn to the fact that using the product for purposes other than those for which it was developed could be dangerous. The figures given are average values and do not represent minimum or maximum values for specific uses. Chemicar Europe cannot be held liable for any defects in the product; the customer is responsible for deciding which type of product he considers suitable for the application in question.