

TDS TECHNICAL DATA SHEET

TECHNICAL DATA SHEET TAP 50/52 - Finixa duc tape 50mm x 50 m 18p. - grey/black

Description

Duc tape TAP 50/52 is premium grade 70 mesh with an aggressive adhesive formula, which makes it suitable for repairing and construction work, etc. The tape has excellent holding power and can be cleanly removed, even after long periods of time. Colours are silver (TAP 50) and black (TAP 52).

Adhesive

- Natural rubber with synthetic resin.
- UV-stabilizing agents
- Color: white

Carrier

- Waterproof, LDPE laminated cloth(65% Polyester + 35% Cotton).
- P/C cloth (70 mesh).

Applications

- Sealing and insulating applications.
- Hole closure, repairing and masking.
- Interior and exterior use.
- Packaging, holding and bundling.

Technical specification

•	Mesh	70 mesh
•	Total thickness	300 +/- 10 μm
•	Tensile strength (Newton/25 mm)	161,8 N
•	Elongation at break	11,5%
•	180° peel adhesion to stainless steel (GR/25 mm)	1000
•	Temperature range	-15 °C -> 50 °C

Application

Temperature: between -5°C and + 35°C. Surface must be clean and free from dust and grease. Avoid touching the tapes exposed adhesive surface in order to keep full adhesive performance. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 HRS at 23 °C.

Storage and shelf life

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Shelf life: 2 years

The above information is given in good faith, but the user should assure himself that the performance of the product is sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Chemicar Europe cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the tapes suitability for their own applications.

T.: +32 3 234 87 80

F.: +32 3 234 87 89

info@chemicar.eu

www.chemicar.eu