












	LA DESCRIPTION	 NOMBRE DE COUCHES	 FLASH ENTRE LES COUCHES (min.)	 ÉPAISSEUR DU FILM SEC	 SÉCHAGE HORS POUSSIÈRES (min.)	 SÉCHAGE (min.)	 SÉCHAGE À L'INFRAROUGE (min.)	 DURÉE DE VIE (année)	 M ² /CAN/LAYER	 PAGE	
APPRÊT	TSP 110 - 120 - 130 - 140	Apprêt	1-2	10	30µm	10	60 - 20°C	10	4	1,5	128
	TSP 1500	Apprêt/filler UV	1-2	20 sec	30-40µm	-	1-2 - UV	-	3	1,5	128
PROTECTION ANTI CORROSION	TSP 190	Apprêt phosphatant	1-2	3-5	15µm	5	20 - 20°C	-	3	-	129
	TSP 410	Bombe de zinc	1-4	10	20-25µm	10	20 - 20°C	-	4	1-2	129
	TSP 810	Apprêt pour soudure Phosphate de zinc	2	5	-	-	15 - 20°C	-	4	-	130
	TSP 530	Apprêt pour soudure à base de cuivre	2	5	-	-	10 - 20°C	-	4	-	130
PEINTURES ET VERNIS	TSP 520 - 525	Aérosol pour jantes gris	2-3	5	-	10	180 - 20°C	possible	4	-	131
	TSP 180	Vernis 1K	2-3	10	30-40µm	10	120	-	4	1,3-1,4 40µm	131
	TSP 1000 - 1010	Haute brillance	-	10	-	10	120	-	2	1,5	131
	TSP 910	Noir Mat	2-3	5	15-20µm	10	300 - 20°C	-	4	1-2	131
2K	TSP 710	Vernis 2K	1-2	10-15	30-50µm	10	720 - 20°C 40 - 60°C	35-40	3	0,5 - 0,75	138
	TSP 720	Mastic pulvérisable 2K	2-5	5	200-450µm	15	300 - 20°C 30 - 60°C	20-40	2	0,25 200µm	138
SPÉCIALES	TSP 030	Primer d'adhésion	Increases the adhesion on plastic. Apply in thin layer. Flash-off 10-15 minutes.							132	
	TSP 310	Guide de ponçage	Can be sanded after 3 seconds without clogging the sanding material.							133	
	TSP 920	Diluant raccord	Solvent for universal blending. Compatible with all A-brand clear coats.							132	
	TSP 550	Spray structure	Restores the structure of damaged external and internal elements. Is paintable.							133	
	TSP 1100	Colle de contact néoprène	Universal, fast-drying spray adhesive.							133	
	AGB - AGG	Spray anti-gravillon	Quick-drying, paintable, anti-chip coating based on synthetic rubber.							134	
	TSP 930	Spray de contrôle	Creates a temporary shine on the sample plate. For colour inspection.							135	
	TSP 100 - 900	Aérosol pré-chargé pour base solvanté	Can be prefilled with propellant. Compatible with most paint brands.							136	